

MARKED-COPY

## A PROCESS OF PREPARING CONTINUOUS FILAMENT COMPOSED OF NANO FIBER

### TECHNICAL FIELD

The present invention relates to a process of preparing a continuous filament or yarn (hereinafter, commonly referred to as a "filament") composed of ~~a~~-nano fibers, and more particularly, to a process of preparing a continuous filament composed of ~~a~~-nano fibers, using an electrospinning method.

In the present invention, the nano fiber ~~designates~~-defines a fiber having a fiber diameter of less than 1,000 nm, more preferably, less than 500 nm.

A woven fabric composed of ~~a~~-nano fibers can be utilized for ~~an~~making artificial leather, filters, diapers, sanitary pads, sutures, antisetting agents, wiping cloth, artificial vessels, bone fixing devices and the like, and is particularly, ~~it is very~~ useful for the production of the artificial leather.

### BACKGROUND ART

As conventional techniques for preparing an ultra fine fiber or nano fiber suitable for the production of an artificial leather, there are known a sea-island type conjugated spinning method, a split type conjugated spinning method, a blend spinning method and ~~so on~~-the like

However, in case of the sea-island type conjugated spinning method or the blend spinning method, one of two polymer components consisting of a fiber must be dissolved and removed ~~for making~~-to make the ultra fine fiber. In order to produce ~~an~~-artificial leather from ~~the~~-fiber prepared by these methods, a complex process must be carried out, including melt spinning, fiber production, non-woven fabric production, urethane impregnation and single component dissolution.

Nevertheless, it ~~was~~-is impossible to produce a fiber with a diameter of less than 1,000 nm by the above two methods.

In case of the spit type conjugate spinning method, it ~~was~~is problematic in that since

two polymer components (for example, a polyester and a polyamide) with different dyeing properties co-exist in a the fiber, uneven dyeing is ~~shown~~ exhibited and ~~an the~~ artificial leather production process is complicated. In addition, it ~~was~~ is difficult to produce a fiber with a diameter less than 2,000 nm by the above method.

Another conventional technique for preparing ~~a-nano fibers~~, an is the electrospinning method ~~is suggested~~. In the electrospinning method, as shown in fig. 4, a polymer spinning dope in a spinning dope main tank (20) is continuously and constantly fed ~~into~~ to a plurality of nozzles (2), to which ~~has~~ a high voltage is applied, through a metering pump (21). Subsequently, the spinning dope fed to the nozzles (2) is spun and collected through the nozzles (2) on a collector (4) of an endless belt type having a high voltage of more than 5 kV, thereby producing a fiber web. The fiber web produced is needle-punched in the next process to produce a non-woven fabric composed of ~~a-nano fibers~~.

5 As seen from above, the conventional electrospinning method can produce only a web or non-woven fabric composed of a nano fiber less than 1,000 nm. Hence, to prepare a continuous filament by the conventional electrospinning method, the produced nano fiber web has to be cut to a predetermined length to produce a staple and this staple has to ~~be~~ undergone an additional spinning process to produce spun yarn, which makes the process complicated.

10 In case of the non-woven fabric composed of ~~a-nano fiber~~, there is a limitation to employing the non-woven fabric to various fields of application, such as the artificial leather, due to the limits in the physical properties of the non-woven fabric. For reference, it is difficult to achieve physical properties of more than 10 MPa from ~~the~~ non-woven fabric composed of ~~a-nano fiber~~.

15 The present invention is intended to prepare a continuous filament composed of ~~a~~ nano fiber ~~with~~ utilizing a simple procedure ~~by~~ of providing a process of continuously preparing a filament (yarn) using ~~an~~ electrically spun nano fiber web, without any additional spinning process. Additionally, the present invention is intended to provide a continuous filament of a nano fiber which is superior in physical properties and is suitable for various industrial materials, such as a filters, diapers, sanitary pads, artificial vessels and so on, as well as

20

5 artificial leather.

## DISCLOSURE OF INVENTION

The present invention has been developed for the purpose of solving the foregoing problems and thus it is an object of the present invention to provide a process of preparing a  
 10 continuous filament composed of a nano fiber, wherein nano fibers are prepared by spinning a polymer spinning dope in a spinning dope main tank (20) onto the surface of water or an organic solvent (4a) ~~of disposed in~~ a collector (4), ~~which contains water or inorganic solvent (4a) and has providing~~ a conductive material (5) with a high voltage applied sunken in the water or organic solvent (4a), through nozzles (2) with a high voltage applied, and the nano  
 15 fibers are pressed, drawn, dried and wound while being pulled by a rotary roller (6) rotating at a constant linear velocity from the location spaced more than 1 cm from one end of a dropping spot.

### Brief Description of the Drawings

~~Hereinafter,~~ ¶The present invention will be described in detail with reference to the  
 20 accompanying drawings-, now wherein,

~~Fig. 1 is a schematic view showing a process of the present invention.-~~

Fig. 1 is a schematic view showing the process of the present invention;

Fig. 2 is an enlarged view of a collector used in the present invention;

Fig. 3 is a schematic view showing a process of spinning two kinds of polymer spinning dopes onto one collector;  
 25

Fig. 4 is a schematic view showing a process of a conventional electrospinning method for preparing a nano fiber web;

Fig. 5 is a scanning electron micrograph of a surface of an undrawn filament (aggregate of nano fibers) prepared according to

30 Example 1; and

Fig. 6 is a scanning electron micrograph of a surface of an undrawn filament (aggregate of nano fibers) prepared according to

Example 5.

5

### Detailed Description of the Invention

Firstly, ~~i~~In the present invention, as shown in ~~f~~Fig. 1, a polymer spinning dope disposed in a spinning dope main tank (20) is ~~constantly-continuously~~ fed into a plurality of nozzles (2) through a metering pump (21). The nozzles (2) have a high voltage of more than 5 kV applied therefor by a voltage generator (1).

Next, the constantly fed polymer spinning dope fed through the plurality of nozzles (2) is electrically spun into spun nano fibers 3 onto the surface of water or an organic solvent (4a) in a collector (4) specifically provided ~~manufactured in the present invention, to thereby~~ collect a nano fiber.

The collector (4) is a container containing water or organic solvent (4a) and has ~~such a~~ construction ~~that whereby~~ a conductive material (5) having a high voltage of more than 5 kV applied thereto by the voltage generator (1) is ~~installed, being sunken-submerged~~ in the water or organic solvent (4a) disposed in the container.

The conductive material (5) is a metal plate or metal powder. The distance (h) from the surface of the water or organic solvent (4a) contained in the collector (4) to the top surface of the conductive material (5) is 0.01 to 200 mm, more preferably, 5 to 50 mm.

If the distance (h) is ~~too-short~~small, the spun nano fiber is ~~directly~~placed in direct contacted with the surface of the conductive material (5) and thereafter ~~is not~~cannot be pulled away well by a rotary roller (6), thereby making the process difficult. If the distance (h) is ~~too long~~large, the voltage applied to the conductive material (5) is not transferred well to the surface of water or organic solvent, thereby making ~~a~~the collected state of the nano fiber very poor.

The diameter of the spun nano fiber is less than 1,000 nm, more preferably, less than 500 nm.

Next, the nano fibers, spun and collected on the surface of the water or organic solvent (4a) contained in the collector (4) are continuously pulled by the rotary roller (6) to thus form an undrawn filament (an aggregate of nano fibers).

~~Whereupon, t~~The angle ( $\theta$ ) between the nano fibers spun and collected on the surface

5 of water or organic solvent (4a) in the collector (4) and the undrawn filament (aggregate of nano fibers) pulled by the rotary roller (6) is 0 to 180°C, more preferably, 10 to 90°C.

The distance (d) from one end of ~~a-the~~ dropping spot of the nano fibers, to the initial point where the nano fibers are pulled by the rotary roller (6) is more than 1 cm. If the distance (d) is less than 1 cm, the spun nano fibers are pulled up in a state ~~that it is~~ where they have not sufficiently coagulated, thereby making the production of a continuous filament more difficult.

Next, the undrawn filament (aggregate of nano fibers) pulled by the rotary roller (6) to tension controlled 7 is pressed by ~~a-~~press rollers (8), (9), (10) and (12) to remove the residual water or organic solvent in the aggregate, then dried by a drier (11) ~~as-after~~ being drawn between drawing rollers (8, 10 and 12) and then are wound by a winding roller (13). The drawn filament may be twisted by a twister before it is wound.

In ~~this-the~~ present invention, an electric spinning process, a process of pulling nano fibers, a pressing process, a drawing process and a drying process are continuously carried out.

The polymer spinning dope of ~~this-the~~ present invention is composed of a polyester resin, nylon resin, a polysulfon resin, a polylactic acid, a copolymer thereof or a mixture thereof.

As shown in ~~f~~Fig. 3, the present invention also includes a method of preparing a filament composed of a hybrid nano fiber by spinning more than two kinds of polymer spinning dope to the surface of water or organic solvent (4a) contained in the same collector (4) through each of the nozzles (2).

Additionally, the present invention also includes a method of preparing a filament composed of ~~a-~~hybrid nano fibers by spinning two kinds of polymer spinning dope ~~by-a~~ with respective nozzles (2) and a respective collector (4) ~~of this invention~~ and then blending ~~the-the~~ two kinds of spun nano fibers ~~of two kinds~~ by pulling them ~~by~~ with the same rotary roller (6).

30 Additionally, the present invention also includes a method of preparing a filament composed of ~~a-~~hybrid nano fibers by twisting two kinds of filaments separately spun, drawn and wound according to the method of the present invention.

## 5 BRIEF DESCRIPTION OF THE DRAWINGS

— These and other features, aspects, and advantages of preferred embodiments of the present invention will be more fully described in the following detailed description, taken accompanying drawings.

In the drawings:-

10 Fig. 1 is a schematic view showing a the process of the present invention;

Fig. 2 is an enlarged view of a collector used in the present invention;

Fig. 3 is a schematic view showing a process of spinning two kinds of polymer spinning dopes onto one collector;

15 Fig. 4 is a schematic view showing a process of a conventional electrospinning method for preparing a nano fiber web;

Fig. 5 is a scanning electron micrograph of a surface of an undrawn filament (aggregate of nano fibers) prepared according to Example 1; and

20 Fig. 6 is a scanning electron micrograph of a surface of an undrawn filament (aggregate of nano fibers) prepared according to Example 5.

~~Explanation of reference numerals for main components in the drawings.~~

- 25 — 1: voltage generator — 2: nozzle (spinneret)
- 3: spun nano fiber — 4: collector
- 4a: water or organic solvent in collector
- 5: conductive material — 6: rotary roller
- 7: tension controller — 8: press roller
- 9, 10, 12: drawing roller — 11: drier
- 30 — 13: winder — 20: spinning dope main tank
- 21: metering pump
- h: distance from surface of water or organic solvent to top surface of conductive material
- d: distance from one end of dropping spot to initial point where nano fibers are pulled

5 ~~—  $\theta$ : angle between nano fibers on surface of water or organic solvent and undrawn filament pulled by rotary roller~~

### BEST MODES FOR CARRYING OUT THE INVENTION

Hereinafter, the present invention will be described in detail with reference to  
10 examples. But, this invention is not limited to the following examples.

#### EXAMPLE 1

A polymer spinning dope was prepared by dissolving a poly( $\epsilon$ -caprolactone) polymer (purchased from Aldrich Chemical Company) having a number average molecular weight of 80,000 in a mixed solvent of methylene chloride/N, N'-dimethyl form amide (volume ratio:  
15 75/25) at a concentration of 13% by weight. The polymer spinning dope had a surface tension of 35 mN/m, a solution viscosity of 35 centipoise at an ambient temperature, an electric conductivity of 0.02 mS/m and a permittivity constant of 90. The polymer spinning dope was constantly fed to 15 nozzles (2) with a 1 mm diameter and a 25 kV voltage applied through a metering pump (21). Then, as shown in FIG. 1, the polymer spinning dope was electrically  
20 spun onto a collector (4) of this invention, which contains water (4a) and has a conductive material (5) of a copper plate with a 25 kV voltage and a 10 mm thickness sunken in the water (4a), more concretely, onto the surface of water contained in the collector (4). The distance (h) from the surface of water to the top surface of the conductive material (5) was 1 cm. Continually, nano fibers spun and agglomerated on the surface of water contained in the  
25 container (4) were pulled by a rotary roller (6) with a linear velocity of 36 m/min to thus prepare an undrawn filament (aggregate of nano fibers). The angle ( $\theta$ ) between the nano fibers located on the water surface and the undrawn filament (aggregate of nano fibers) pulled by the rotary roller (6) was 30°. The distance (d) from one end of a dropping spot of the nano fibers to the initial point where the nano fibers are pulled by the rotary roller (6) was 5 cm.  
30 The thusly prepared undrawn filament (aggregate of nano fibers) had a fineness of 108 deniers, a strength of 0.22 g/d and an elongation of 106%, and an electron micrograph of the surface thereof is as shown in FIG. 5. Continually, the undrawn filament (aggregate of nano fibers) having passed through the rotary roller was pressed by a press roller (9), dried by a

5 drier (11) while being drawn by drawing rollers (8, 10 and 12) so that the total draw ratio becomes 1.4 and then wound by a winding roller (13), thereby preparing a continuous filament composed of a nano fiber. The finally prepared continuous filament (composed of a nano fiber and drawn) had a strength of 1.4 g/d and an elongation of 35%.

### EXAMPLE 2

10 A polymer spinning dope was prepared by dissolving a nylon-6 resin, which has a relative viscosity of 3.2 in a 96% sulfuric acid solution, in a form acid at a concentration of 15% by weight. The polymer spinning dope had a surface tension of 49 mN/m, a solution viscosity of 40 centipoise at an ambient temperature and an electric conductivity of 420 mS/m. The polymer spinning dope was constantly fed to 15 nozzles (2) with a 1 mm diameter and a 30  
15 kV voltage applied through a metering pump (21). Then, as shown in fig. 1, the polymer spinning dope was electrically spun onto a collector (4) of this invention, which contains water (4a) and having a conductive material (5) of a copper plate with a 30 kV voltage and a 20 mm thickness sunken in the water (4a), more concretely, onto the surface of water contained in the collector (4). The distance (h) from the surface of water to the top surface of  
20 the conductive material (5) was 1 cm. Continually, nano fibers spun and agglomerated on the surface of water were pulled by a rotary roller (6) with a linear velocity of 30 m/min to thus prepare an undrawn filament (aggregate of nano fibers). The angle ( $\theta$ ) between the nano fibers located on the water surface and the undrawn filament (aggregate of nano fibers) pulled by the rotary roller (6) was 40°. The distance (d) from one end of a dropping spot of the nano fibers  
25 to the initial point where the nano fibers are pulled by the rotary roller (6) was 8 cm. The prepared undrawn filament (aggregate of nano fibers) had a fineness of 110 deniers, a strength of 0.56 g/d and an elongation of 205%. Continually, the undrawn filament (aggregate of nano fibers) having passed through the rotary roller was pressed by a press roller (9), dried by a  
30 drier (11) while being drawn by drawing rollers (8, 10 and 12) so that the total draw ratio becomes 2.8 and then wound by a winding roller (13), thereby preparing a continuous filament composed of a nano fiber. The finally prepared continuous filament (composed of a nano fiber and drawn) had a strength of 2.8 g/d and an elongation of 35%.

### EXAMPLE 3



5           A polyester spinning dope (hereinafter, referred to as a spinning dope B) was prepared  
 by dissolving a polyester resin with an intrinsic viscosity of 0.64 in a mixed solvent of  
 trifluoro acetic acid/methylene chloride (volume ratio: 50/50) at a concentration of 15% by  
 weight. The nylon-6 spinning dope (hereinafter, referred to as a "spinning dope A") of  
 Example 2 and the spinning dope B were constantly fed to 15 nozzles (2) with a 1 mm  
 10 diameter and a 25 kV voltage applied alternately through a metering pump (21). Then, as  
 shown in fig. 1, the spinning dope A and the spinning dope B were electrically spun onto a  
 collector (4) of this invention, which contains water (4a) and has a conductive material (5) of  
 a copper plate with a 25 kV voltage and a 10 mm thickness sunken in the water (4a), more  
 concretely, onto the surface of water contained in the collector (4). The distance (h) from the  
 15 surface of water to the top surface of the conductive material (5) was 1 cm. Continually, nano  
 fibers spun and agglomerated on the surface of water were pulled by a rotary roller (6) with a  
 linear velocity of 20 m/min to thus prepare a hybrid undrawn filament (aggregate of nano  
 fibers). The angle ( $\theta$ ) between the nano fibers located on the water surface and the hybrid  
 undrawn filament (aggregate of nano fibers) pulled by the rotary roller (6) was 30°. The  
 20 distance (d) from one end of a dropping spot of the nano fibers to the initial point where the  
 nano fibers are pulled by the rotary roller (6) was 5 cm. Continually, the undrawn filament  
 (aggregate of nano fibers) having passed through the rotary roller was pressed by a press roller  
 (9), dried by a drier (11) while being drawn by drawing rollers (8, 10 and 12) so that the total  
 draw ratio becomes 3.0 and then wound by a winding roller (13), thereby preparing a  
 25 continuous filament composed of a hybrid nano fiber. The finally prepared continuous  
 filament (composed of a nano fiber and drawn) had a strength of 2.7 g/d and an elongation of  
 46%.

#### EXAMPLE 4

30           A polymer spinning dope was prepared by dissolving a polyvinyl alcohol (purchased  
 from Celanese) having a number average molecular weight of 65,000 and a viscosity  
 of 96% in a 80° C. distilled water at a concentration of 10% by weight and adding  
 phosphoric acid therein so that the polyvinyl alcohol has a pH 2.5. The polymer  
 spinning dope was constantly fed to 15 nozzles (2) with a 1mm diameter and a 20 kV

5 voltage applied through a metering pump (21). Then, as shown in fig. 1, the polymer  
 spinning dope was electrically spun onto a collector (4) of this invention, which  
 contains ethanol (4a) and having a conductive material (5) of a copper plate with a 20  
 kV voltage and a 20 mm thickness sunken in the ethanol (4a), more concretely, onto  
 the surface of ethanol contained in the collector (4). The distance (h) from the surface  
 10 of ethanol to the top surface of the conductive material (5) was 1 cm. Continually,  
 nano fibers spun and agglomerated on the surface of ethanol were pulled by a rotary  
 roller (6) with a linear velocity of 30 m/min to thus prepare an undrawn filament  
 (aggregate of nano fibers). The angle ( $\theta$ ) between the nano fibers located on the  
 ethanol surface and the undrawn filament (aggregate of nano fibers) pulled by the  
 15 rotary roller (6) was 30°. The distance (d) from one end of a dropping spot of the nano  
 fibers to the initial point where the nano fibers are pulled by the rotary roller (6) was  
 10 cm. Continually, the undrawn filament (aggregate of nano fibers) having passed  
 through the rotary roller was pressed by a press roller (9), dried by a drier (11) while  
 being drawn by drawing rollers (8, 10 and 12) so that the total draw ratio becomes 2.0  
 20 and then wound by a winding roller (13), thereby preparing a continuous filament  
 composed of a nano fiber. The finally prepared continuous filament (composed of a  
 nano fiber and drawn) had a strength of 1.5 g/d and an elongation of 45%. The average  
 diameter of the nano fiber was 250 nm.

#### EXAMPLE 5

25 A polymer spinning dope was prepared by dissolving a polyurethane resin having a  
 molecular weight of 80,000 in a mixed solvent of dimethyl formamide/tetrahydrofuran  
 (volume ratio: 5/5) at a concentration of 13.5% by weight. The polymer spinning dope was  
 constantly fed to 15 nozzles (2) with a 1 mm diameter and a 30 kV voltage applied through a  
 metering pump (21). Then, as shown in fig. 1, the polymer spinning dope was electrically  
 30 spun onto a collector (4) of this invention, which contains water (4a) and having a conductive  
 material (5) of a copper plate with a 30 kV voltage and a 10 mm thickness sunken in the water  
 (4a), more concretely, onto the surface of water contained in the collector (4). The distance (h)  
 from the surface of water to the top surface of the conductive material (5) was 1.5 cm.

Continually, nano fibers spun and agglomerated on the surface of water were pulled by a rotary roller (6) with a linear velocity of 36 m/min to thus prepare an undrawn filament (aggregate of nano fibers). The angle ( $\theta$ ) between the nano fibers located on the water surface and the undrawn filament (aggregate of nano fibers) pulled by the rotary roller (6) was  $30^\circ$ . The distance (d) from one end of a dropping spot of the nano fibers to the initial point where the nano fibers are pulled by the rotary roller (6) was 10 cm. The thusly prepared undrawn filament (aggregate of nano fibers) had a fineness of 63.5 deniers, a strength of 0.5 g/d and an elongation of 106%, and an electron micrograph of the surface thereof is as shown in fig. 6. Continually, the undrawn filament (aggregate of nano fibers) having passed through the rotary roller was pressed by a press roller (9), dried by a drier (11) while being drawn by drawing rollers (8, 10 and 12) so that the total draw ratio becomes 1.4 and then wound by a winding roller (13), thereby preparing a continuous filament composed of a nano fiber. The finally prepared continuous filament (composed of a nano fiber and drawn) had a strength of 1.2 g/d and an elongation of 80%.

## INDUSTRIAL APPLICABILITY

The present invention ~~can prepare~~ produces a continuous filament composed of a nano fibers by a simpler, continuous procedure. The continuous filament prepared according to the present invention is greatly improved in physical properties, and thus it is useful as materials ~~of in~~ various industrial fields, such as an artificial dialyzing filter, artificial vessel, anti-adhesion agent, artificial bone and so on, as well as daily necessities, such as an artificial leather, air cleaning filters, wiping cloth, golf glove, wig and so on.